

## Tolerance on sheet thickness according to DIN EN ISO 14632

Thickness	Min. Tolerance	Max. Tolerance	Tolerance
0.50	0.48	0.58	-0.02 / +0.08
0.80	0.75	0.70	-0.05 / +0.10
1.00	0.90	1.10	-0.10 / +0.10
1.50	1.65	1.35	-0.15 / +0.15
2.00	1.85	2.15	-0.15 / +0.15
2.50	2.35	2.65	-0.15 / +0.15
3.00	2.80	3.20	-0.20 / +0.20
4.00	3.80	4.20	-0.20 / +0.20
5.00	4.75	5.25	-0.25 / +0.25
6.00	5.75	6.25	-0.25 / +0.25
8.00	7.80	8.90	-0.20 / +0.90
10.00	10.20	10.90	+0.20 / +0.90
12.00	12.30	13.50	+0.30 / +1.50
15.00	15.30	16.50	+0.30 / +1.50
20.00	20.30	21.50	+0.30 / +1.50
25.00	25.30	26.50	+0.30 / +1.50
30.00	30.50	32.50	+0.50 / +2.50
35.00	35.50	37.50	+0.50 / +2.50
40.00	40.50	42.50	+0.50 / +2.50
50.00	50.50	52.50	+0.50 / +2.50

All dimensions are in millimeters (mm)